

EPODURE VY300

Vinylester Styrene-Free Anchor Resin

DESCRIPTION

EPODURE VY300 is a two-component Vinylester styrene-free chemical anchor system. It utilizes the latest covalent bond technology and is particularly suitable for use in confined spaces due to its styrene-free properties. It is a fast curing high strength product suitable for high loads and critical overhead fixings.

USES

EPODURE VY300 is particularly suitable for bonding of resin anchors. It is a fast curing resin that is particularly suitable for bonding to low strength substrates.

ADVANTAGES

- Suitable for use in corrosive environments.
- Damp tolerable.
- Rapid curing time.
- Suitable for critical overhead application.
- Low shrinkage values.
- Close edge distance and small spacing.

Property	Value
Compressive Strength	84 MPa
Flexural Strength	27 MPa
Flexural Modulus	3789
Tensile Strength	13.7
E Modulus	10560

PROCEDURE

Surface Preparation: The hole should be drilled to the appropriate depth using a suitable sized drill bit. The hole must be free from all dust, debris and other deleterious material. An air pump should be used by inserting to the full depth of the hole before pumping at least 4 times, use an extension nozzle if required. The hole should then be brushed using a suitable pour hole

brush, this bit should be carried out in a twisting motion, before removing and re-inserting 4 times. The hole should then be blown out again using the air pump at least 4 times.

Application: The nozzle of the cartridge should be inserted onto the tube. The cartridge should be inserted into the appropriate gun before extruding a minimum of 12ml of mixed material. This should be discarded before pumping the resin into the hole. It is important to ensure that the process is carried out before applying resin from a new tube. EPODURE VY300 should be injected to the back of the hole slowly withdrawing the nozzle as the hole fills. The threaded rod or reinforcement bar should be inserted into the hole, twisting slowly as it is inserted, to ensure maximum bond to the steel. It is important to leave the grouted component undisturbed until sufficiently cured.

Temperature	Working Time	Cure Time in Dry Concrete
-10°C	60 mins	180 mins
-5°C	50 mins	90 mins
5°C	20 mins	30 mins
15°C	7 mins	20 mins
25°C	6 mins	20 mins
35°C	3 mins	20 mins

These figures are based on M12 fixings and the resin temperature must be at least 20°C.

PACKAGING & COVERAGE

Pack Size: EPODURE VY300 is supplied in 345ml cartridges, there are 12 cartridges per box.

STORAGE & SHELF LIFE

EPODURE VY300 should be stored in unopened containers at temperatures between 60C and 300C. When stored in unopened containers, it will have a shelf life of 12 months.

HEALTH & SAFETY

See separate material safety datasheet.



THE FOLLOWING TABLES OF DATA HAVE BEEN TAKEN FROM THE EUROPEAN TECHNICAL ASSESSMENT ETA-18/1127. THE DATA SHOWN BELOW IS A GUIDE AND, IN ALL INSTANCES, REFERENCE SHOULD BE MADE TO THE ETA WHICH OVERRIDES THE DATA SHOWN BELOW AND MAY BE FOUND ON THE FOLLOWING WEBSITE: www.etadanmark.dk

LOADS, EDGE AND SPACINGS BASED ON CHARACTERISTIC BOND STRENGTHS - SHOWING STEEL FAILURE

Size (mm)	Characteristic Resistance (kN)		Design Resistance (kN)		Recommended Load (kN)		Characteristic distances (mm)			Min Edge and Spacing (mm)	Nominal Embedment (mm)	Hole Diameter concrete (mm)	Hole Diameter fixture (mm)	Max Torque (Nm)
	Tension N_{rk}	Shear V_{rk}	Tension N_{rd}	Shear V_{rd}	Tension N_{rec}	Shear V_{rec}	Edge $C_{cr,N}$	Spacing $S_{cr,N}$	Edge $C_{cr,V}$					
8	19,00		12,70		9,07						60			
	19,00	9,00	12,70	7,20	9,07	5,14	80	160	80	40	80	10	9	10
	19,00		12,70		9,07						160			
10	22,62		15,08		10,77						60			
	30,20	15,00	20,10	12,00	14,36	8,57	100	200	90	50	90	12	12	20
	30,20		20,10		14,36						200			
12	29,82		19,88		14,20						70			
	43,80	21,00	29,20	16,80	20,86	12,00	120	240	110	60	110	14	14	40
	43,80		29,20		20,86						240			
16	43,43		28,95		20,68						80			
	67,86	39,00	45,24	31,20	32,31	22,29	160	320	125	80	125	18	18	80
	81,60		54,40		38,86						320			
20	55,42		36,95		26,39						90			
	104,68	61,00	69,79	48,80	49,85	34,86	200	400	180	100	170	24	22	120
	127,40		84,90		60,64						400			
24	63,33		42,22		30,16						100			
	133,00	88,00	88,67	70,40	63,33	50,29	230	460	220	120	210	28	26	160
	183,60		122,40		87,43						480			
27	70,91		47,27		33,77						110			
	154,72	115,00	103,15	92,00	73,68	65,71	270	540	240	135	240	32	30	180
	238,00		159,10		113,64						540			
30	78,04		52,02		37,16						120			
	182,09	142,50	121,39	114,00	86,71	81,43	280	560	280	150	280	35	32	200
	292,00		194,50		138,93						600			
33	88,95		59,30		42,36						130			
	205,27	173,50	136,85	138,80	97,75	121,43	310	620	310	165	300	37	36	250
	360,00		240,60		171,86						660			
36	108,57		72,38		51,70						150			
	246,10	212,50	164,07	170,00	117,19	121,43	330	660	330	180	340	40	38	300
	425,00		283,33		202,38						720			

DESIGN RESISTANCE USED WITH VARIOUS STUD STRENGTHS, MATERIAL AND REBAR.

5.8 Grade Steel Studding

Stud Diameter (mm)	Hole Diameter (mm)	Embedment Depth h _{ef}																				h _{ef} failure (mm)	F _{da} design load (kN)
		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		
8	10	12,7																				59	12,7
10	12	15,1	17,6	20,1																		80	20,1
12	14		19,9	22,7	25,6	28,4	29,2															103	29,2
16	18			29,0	32,6	36,2	39,8	43,4	47,1	50,7	54,4											150	54,4
20	24			32,8	36,9	41,1	45,2	49,3	53,4	57,5	65,7	82,1	84,9									207	84,9
24	28				42,2	46,5	50,7	54,9	59,1	67,6	84,5	101,3	118,2	122,4								290	122,4
27	32					47,3	51,6	55,9	60,2	68,8	86,0	103,2	120,3	137,5	159,1							370	159,1
30	35						52,0	56,4	60,7	69,4	86,7	104,1	121,4	138,8	173,4	195						449	194,5
33	38							59,3	63,9	73,0	91,2	109,5	127,7	146,0	182,5	219,0	241					527	240,6
36	40								67,6	77,2	96,5	115,8	135,1	154,4	193,0	231,6	260,6	283				587	283,2
Depth (mm)		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		

8.8 Grade Steel Studding

Stud Diameter Diameter (mm)	Hole Diameter Diameter (mm)	Embedment Depth h _{ef}																				h _{ef} failure (mm)	F _{da} design load (kN)
		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		
8	10	12,9	15,0	17,2	19,3	19,5																91	19,5
10	12	15,1	17,6	20,1	22,6	25,1	27,6	30,2	30,9													123	30,9
12	14		19,9	22,7	25,6	28,4	31,2	34,1	36,9	39,8	45,0											158	45,0
16	18			29,0	32,6	36,2	39,8	43,4	47,1	50,7	57,9	72,4	83,7									231	83,7
20	24			32,8	36,9	41,1	45,2	49,3	53,4	57,5	65,7	82,1	98,5	114,9	130,7							318	130,7
24	28				42,2	46,5	50,7	54,9	59,1	67,6	84,5	101,3	118,2	135,1	168,9	188,3						446	188,3
27	32					47,3	51,6	55,9	60,2	68,8	86,0	103,2	120,3	137,5	171,9	206,3	232,1					570	244,8
30	35						52,0	56,4	60,7	69,4	86,7	104,1	121,4	138,8	173,4	208,1	234,1	260,2				690	299,2
33	38							59,3	63,9	73,0	91,2	109,5	127,7	146,0	182,5	219,0	246,4	273,7	301,1			811	370,1
36	40								67,6	77,2	96,5	115,8	135,1	154,4	193,0	231,6	260,6	289,5	318,5	347,4		903	435,7
Depth (mm)		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		

10.9 Grade Steel Studding

Stud Diameter (mm)	Hole Diameter (mm)	Embedment Depth h _{ef}																				h _{ef} failure (mm)	F _{da} design load (kN)
		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		
8	10	12,9	15,0	17,2	19,3	21,4	23,6	25,7	27,2													127	27,2
10	12	15,1	17,6	20,1	22,6	25,1	27,6	30,2	32,7	35,2	40,2	43,1										171	43,1
12	14		19,9	22,7	25,6	28,4	31,2	34,1	36,9	39,8	45,4	56,8	62,6									220	62,6
16	18			29,0	32,6	36,2	39,8	43,4	47,1	50,7	57,9	72,4	86,9	101,3	115,8	116,6						322	116,6
20	24			32,8	36,9	41,1	45,2	49,3	53,4	57,5	65,7	82,1	98,5	114,9	131,4	164,2						443	182,0
24	28				42,2	46,5	50,7	54,9	59,1	67,6	84,5	101,3	118,2	135,1	168,9	202,7						621	262,2
27	32					47,3	51,6	55,9	60,2	68,8	86,0	103,2	120,3	137,5	171,9	206,3	232,1					793	341,0
30	35						52,0	56,4	60,7	69,4	86,7	104,1	121,4	138,8	173,4	208,1	234,1	260,2				961	416,7
33	38							59,3	63,9	73,0	91,2	109,5	127,7	146,0	182,5	219,0	246,4	273,7	301,1			1130	515,5
36	40								67,6	77,2	96,5	115,8	135,1	154,4	193,0	231,6	260,6	289,5	318,5	347,4		1258	606,9
Depth (mm)		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		

A4-70 Stainless Steel Studding

Stud Diameter	Hole Diameter	steel failure																				h _{ef} failure (mm)	F _{ds} design load (kN)
		Embedment Depth h _{ef}																					
(mm)	(mm)	60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		
8	10	12,9	13,7																			64	13,7
10	12	15,1	17,6	20,1	21,7																	86	21,7
12	14		19,9	22,7	25,6	28,4	31,2	31,6														111	31,6
16	18			29,0	32,6	36,2	39,8	43,4	47,1	50,7	57,9	58,8										162	58,8
20	24			32,8	36,9	41,1	45,2	49,3	53,4	57,5	65,7	82,1	91,7									223	91,7
24	28				42,2	46,5	50,7	54,9	59,1	67,6	84,5	101,3	118,2	132,1								313	132,1
27	32					47,3	51,6	55,9	60,2	68,8	80,2											187	80,2
30	35						52,0	56,4	60,7	69,4	86,7	98,1										226	98,1
33	38							59,3	63,9	73,0	91,2	109,5	121									266	121,3
36	40								67,6	77,2	96,5	115,8	135,1	143								296	142,8
Depth (mm)		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		

A4-80 Stainless Steel Studding

Stud Diameter (mm)	Hole Diameter (mm)	Embedment Depth h _{ef}																				h _{ef} failure (mm)	F _{ds} design load (kN)
		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		
8	10	12,9	15,0	15,7																	73	15,7	
10	12		17,6	20,1	22,6	24,8															99	24,8	
12	14		19,9	22,7	25,6	28,4	31,2	34,1	36,1												127	36,1	
16	18			29,0	32,6	36,2	39,8	43,4	47,1	50,7	57,9	67,2									186	67,2	
20	24			32,8	36,9	41,1	45,2	49,3	53,4	57,5	65,7	82,1	98,5	104,8							255	104,8	
24	28				42,2	46,5	50,7	54,9	59,1	67,6	84,5	101,3	118,2	132,1							313	132,1	
27	32					47,3	51,6	55,9	60,2	68,8	80,2										187	80,2	
30	35						52,0	56,4	60,7	69,4	86,7	98,1									226	98,1	
33	38							59,3	63,9	73,0	91,2	109,5	121,3								266	121,3	
36	40								67,6	77,2	96,5	115,8	135,1	142,8							296	142,8	
Depth (mm)		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	480	540	600	660	720		

High bond reinforcing bars F_{yk}=500N/mm²

Rebar Diameter Diameter	Hole Diameter	Embedment Depth h _{ef}																				h _{ef} failure (mm)	F _{ds} yield load (kN)
		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	500	560	640	720	800		
(mm)	(mm)	80	100	120	140	160	180	200	220	240	260	280	300	320	340	360	380	400	420	440	460		
8	12	8,7	10,2	11,7	13,1	14,6	16,0	17,5	19,0	20,4	21,9												
10	14	10,4	12,1	13,8	15,6	17,3	19,0	20,7	22,5	24,2	27,6	34,1											
12	16		13,7	15,7	17,6	19,6	21,6	23,5	25,5	27,4	31,4	39,2	47,1	49,2									
16	20			19,3	21,7	24,1	26,5	29,0	31,4	33,8	38,6	48,3	57,9	67,6	77,2								
20	25				21,0	23,6	26,2	28,9	31,5	34,1	36,7	42,0	52,5	63,0	73,5	84,0	105,0						
25	30					28,3	31,1	33,9	36,8	39,6	45,2	56,6	67,9	79,2	90,5	113,1	141,4						
28	35						33,4	36,4	39,5	42,5	48,6	60,7	72,8	85,0	97,1	121,4	151,8	170,0					
32	40							43,1	46,5	53,1	66,4	79,6	92,9	106,2	132,7	165,9	185,8	212,3					
36	44								52,3	59,7	74,7	89,6	104,5	119,4	149,3	186,6	209,0	238,9	268,8				
40	50									66,4	82,9	99,5	116,1	132,7	165,9	207,4	232,3	265,4	298,6	331,8			
Depth (mm)		60	70	80	90	100	110	120	130	140	160	200	240	280	320	400	500	560	640	720	800		

CHARACTERISTIC AND DESIGN LOAD RESISTANCES BASED ON CHARACTERISTIC BOND STRENGTHS FOR HEF 4D (MINIMUM EMBEDMENT) TO 20D

	Non Cracked Concrete						Cracked Concrete						Nominal Embed-ment
	Characteristic Resistance (kN)		Design Resistance (kN)		Recommended Load (kN)		Characteristic Resistance (kN)		Design Resistance (kN)		Recommended Load (kN)		
Size (mm)	Tension	Shear	Tension	Shear	Tension	Shear	Tension	Shear	Tension	Shear	Tension	Shear	(mm)
	N _{rk}	V _{rk}	N _{rd}	V _{rd}	N _{rec}	V _{rec}	N _{rk}	V _{rk}	N _{rd}	V _{rd}	N _{rec}	V _{rec}	
8	19,30	9,00	12,87	7,20	9,19	5,14	Not Applicable		Not Applicable		Not Applicable		60
	25,74		17,16		12,26								80
	51,47		34,31		24,51								160
10	22,62	15,00	15,08	12,00	10,77	8,57	10,40	15,00	6,94	12,00	4,96	8,57	60
	33,93		22,62		16,16		15,60		10,40		7,43		90
	75,40		50,27		35,90		34,68		23,12		16,52		200
12	29,82	21,00	19,88	16,80	14,20	12,00	13,12	21,00	8,75	16,80	6,24	12,00	70
	46,86		31,24		22,31		20,62		13,75		9,82		110
	102,24		68,16		48,69		44,98		29,98		21,42		240
16	43,43	39,00	28,95	31,20	20,68	22,29	17,37	39,00	11,58	31,20	8,27	22,29	80
	67,86		45,24		32,31		27,14		18,10		12,93		125
	173,72		115,81		82,72		69,50		46,33		33,10		320
20	55,42	61,00	36,95	48,80	26,39	34,86	21,06	61,00	14,04	48,80	10,00	34,86	90
	104,68		69,79		49,85		39,78		26,52		18,94		170
	246,30		164,20		117,29		93,60		62,40		44,59		400
24	63,33	88,00	42,22	70,40	30,16	50,29	Not Applicable		Not Applicable		Not Applicable		100
	133,00		88,67		63,33								210
	304,01		202,67		144,76								480
27	70,91	115,00	47,27	92,00	33,77	65,71	Not Applicable		Not Applicable		Not Applicable		110
	154,72		103,15		73,68								240
	348,11		232,08		165,77								540
30	78,04	142,50	52,02	114,00	37,16	81,43	Not Applicable		Not Applicable		Not Applicable		120
	182,09		121,39		86,71								280
	390,19		260,12		185,80								600
33	88,95	173,50	59,30	138,80	42,36	99,14	Not Applicable		Not Applicable		Not Applicable		130
	205,27		136,85		97,75								300
	451,60		301,07		215,05								660
36	108,57	212,50	72,38	170,00	51,70	121,43	Not Applicable		Not Applicable		Not Applicable		150
	246,10		164,07		117,19								340
	521,15		347,44		248,17								720

BOND STRENGTH FACTORS

Influence of concrete strength on combined pull out and concrete cone resistance

Concrete Strength N/mm ² (Mpa)	C15/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
non cracked f_c =	0,94	1,00	1,06	1,12	1,17	1,23	1,26	1,30
cracked f_c =	0,96	1,00	1,03	1,05	1,06	1,07	1,08	1,09

Influence of environmental conditions in non cracked concrete

		M8	M10	M12	M16	M20	M24	M27	M30	M33	M36
Temp I 40°C / 24°C	Dry and Wet	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00
Temp II 80°C / 50°C	Dry and Wet	0,90	0,88	0,87	0,86	0,85	0,84	0,83	0,82	0,81	0,80

Influence of environmental conditions in cracked concrete

		M8	M10	M12	M16	M20	M24	M27	M30
Temp I 40°C / 24°C	Dry and Wet	n/a	0,46	0,44	0,40	0,38	n/a	n/a	n/a
Temp II 80°C / 50°C	Dry and Wet	n/a	0,45	0,43	0,40	0,38	n/a	n/a	n/a

CHARACTERISTIC AND DESIGN LOAD RESISTANCES FOR REBAR BASED ON CHARACTERISTIC BOND STRENGTHS FOR HEF 4D (MIN EMBEDMENT) TO 20D

	Non Cracked Concrete						Cracked Concrete						Nominal Embedment						
	Characteristic Resistance (kN)		Design Resistance (kN)		Recommended Load (kN)		Characteristic Resistance (kN)		Design Resistance (kN)		Recommended Load (kN)								
Rebar	Tension	Shear	Tension	Shear	Tension	Shear	Tension	Shear	Tension	Shear	Tension	Shear	(mm)						
Ø	N _{rk}	V _{rk}	N _{rd}	V _{rd}	N _{rec}	V _{rec}	N _{rk}	V _{rk}	N _{rd}	V _{rd}	N _{rec}	V _{rec}							
8	15,68	13,95	8,71	9,30	6,22	6,64	Not Applicable		Not Applicable		Not Applicable		60						
	20,91		11,62		8,30								80						
	41,82		23,23		16,60								160						
10	18,66	21,45	10,37	14,30	7,41	10,21							Not Applicable		Not Applicable		Not Applicable		60
	27,99		15,55		11,11														90
	62,20		34,56		24,68														200
12	24,70	31,05	13,72	20,70	9,80	14,79	10,56	31,05	5,86	20,70	4,19	14,79							70
	38,82		21,56		15,40		16,59		9,22		6,58								110
	84,69		47,05		33,61		36,19		20,11		14,36								240
14	31,67	42,45	17,59	28,30	12,57	20,21	13,72	42,45	7,62	28,10	5,45	20,07	80						
	45,52		25,29		18,06		19,73		10,96		7,83		115						
	110,84		61,58		43,98		48,03		26,68		19,06		280						
16	34,74	55,50	19,30	37,00	13,79	26,43	15,28	55,50	8,49	37,00	6,06	26,43	80						
	54,29		30,16		21,54		23,88		13,26		9,47		125						
	138,97		77,21		55,15		61,12		33,96		24,26		320						
18	37,55	69,66	20,86	46,44	14,90	33,17	16,51	69,66	9,17	46,44	6,55	33,17	80						
	70,40		39,11		27,94		30,96		17,20		12,29		150						
	168,97		93,87		67,05		74,31		41,28		29,49		360						
20	36,76	86,55	20,42	57,70	14,59	41,21	19,79	86,55	11,00	57,70	7,85	41,21	90						
	69,43		38,57		27,55		37,39		20,77		14,84		170						
	163,36		90,76		64,83		87,96		48,87		34,91		400						
22	44,92	104,01	24,96	69,34	17,83	49,53	24,19	104,00	13,44	69,34	9,60	49,53	100						
	85,36		47,42		33,87		45,96		25,53		18,24		190						
	197,67		109,82		78,44		106,44		59,13		42,24		440						
25	51,05	135,00	28,36	90,00	20,26	64,29	27,49	135,00	15,27	90,00	10,91	64,29	100						
	107,21		59,56		42,54		57,73		32,07		22,91		210						
	255,26		141,81		101,29		137,45		76,36		54,54		500						
28	61,08	168,75	33,93	112,50	24,24	80,36	Not Applicable		Not Applicable		Not Applicable		112						
	152,71		84,84		60,60								280						
	305,41		169,67		121,20								560						
32	77,21	220,95	42,89	147,30	30,64	105,21							Not Applicable		Not Applicable		Not Applicable		128
	193,02		107,23		76,60														320
	386,04		214,47		153,19														640

BOND STRENGTH FACTORS – REBAR

Influence of concrete strength on combined pull out and concrete cone resistance

Concrete Strength N/mm ² (MPa)	C15/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/55	C50/60
non cracked f_c =	0,94	1,00	1,06	1,12	1,17	1,23	1,26	1,30
cracked f_c =	0,96	1,00	1,03	1,05	1,06	1,07	1,08	1,09

Influence of environmental conditions in non cracked concrete

		Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 18	Ø 20	Ø 22	Ø 25	Ø 28	Ø 32
Temp I 40°C / 24°C	Dry and Wet	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00	1,00
Temp II 80°C / 50°C	Dry and Wet	0,90	0,90	0,88	0,88	0,88	0,86	0,86	0,86	0,86	0,84	0,84

Influence of environmental conditions in cracked concrete

		Ø 8	Ø 10	Ø 12	Ø 14	Ø 16	Ø 18	Ø 20	Ø 22	Ø 25	Ø 28	Ø 32
Temp I 40°C / 24°C	Dry and Wet	n/a	n/a	0,43	0,43	0,43	0,43	0,53	0,53	0,53	n/a	n/a
Temp II 80°C / 50°C	Dry and Wet	n/a	n/a	0,38	0,38	0,38	0,38	0,46	0,46	0,46	n/a	n/a

MATERIAL PROPERTIES FOR GRADES OF OTHER THREADED ROD AND REBAR

Stud Diameter (mm)	Stud Grade 8.8		Stud Grade 10.9		Stud Grade A4-70		Stud Grade A4-80	
	$N_{rk, s}$	$N_{rd, s}$	$N_{rk, s}$	$N_{rd, s}$	$N_{rk, s}$	$N_{rd, s}$	$N_{rk, s}$	$N_{rd, s}$
	(kN)	(kN)	(kN)	(kN)	(kN)	(kN)	(kN)	(kN)
M8	29,2	19,5	38,1	27,2	25,6	13,7	29,2	15,6
M10	46,4	30,9	60,3	43,1	40,6	21,7	46,4	24,8
M12	67,4	44,9	87,7	62,6	59,0	31,6	67,4	36,0
M16	125,6	83,7	163,0	116,4	109,9	58,8	125,7	67,2
M20	196,1	130,7	255,0	182,1	171,5	91,7	196,0	104,8
M24	282,5	188,3	367,0	262,1	247,1	132,1	293,0	132,1
M27	367,0	244,7	477,4	341,0	229,4	80,2	229,4	80,2
M30	448,8	299,2	583,0	416,4	280,6	98,1	280,6	98,1
M36	653,6	435,7	849,7	606,9	408,4	142,8	408,4	142,8

*1
*1
*1

Stud Diameter (mm)	Stud Grade 8.8		Stud Grade 10.9		Stud Grade A4-70		Stud Grade A4-80	
	$V_{rk, s}$	$V_{rd, s}$	$V_{rk, s}$	$V_{rd, s}$	$V_{rk, s}$	$V_{rd, s}$	$V_{rk, s}$	$V_{rd, s}$
	(kN)	(kN)	(kN)	(kN)	(kN)	(kN)	(kN)	(kN)
M8	14,6	11,7	19,0	15,2	12,8	8,2	14,6	9,4
M10	23,2	18,6	30,2	24,1	20,3	13,0	23,2	14,9
M12	33,7	27,0	43,8	35,1	29,5	18,9	33,7	21,6
M16	62,8	50,2	81,6	65,3	55,0	35,2	62,8	40,3
M20	98,0	78,4	127,4	101,9	85,8	55,0	98,0	62,8
M24	141,2	113,0	183,6	146,8	123,6	79,2	141,2	90,5
M27	183,5	146,8	238,7	191,0	114,7	48,4	114,7	48,4
M30	224,4	179,5	291,5	215,9	140,3	59,2	140,3	59,2
M36	326,8	261,4	424,8	283,2	204,2	86,2	204,2	86,2

Rebar Diameter (mm)	Rebar BSt 500 to DIN 488		Rebar BSt 500 to DIN 488	
	N _{rk, s}	N _{rd, s}	V _{rk, s}	V _{rd, s}
	(kN)	(kN)	(kN)	(kN)
8	28,0	20,0	14,0	9,3
10	43,0	30,7	21,5	14,3
12	62,0	44,3	31,0	20,7
14	84,4	67,0	42,5	28,3
16	111,0	79,3	55,5	37,0
18	139,5	100,0	70,0	46,7
20	173,0	123,6	86,5	57,7
22	208,3	149,3	104,5	69,7
25	270,0	192,9	135,0	90,0
28	339,0	242,1	169,0	112,7
32	442	315,7	221	147,3
36	563,2	443,5	281,6	187,7
40	693,8	546,3	346,9	231,3

EFFECT OF EDGE DISTANCE – SHEAR

Anchor Spacing	Stud / Rebar Diameter											
(mm)	8	10	12	16	20	24	27	30	33	36	40	
40	0,64											
50	0,67	0,63										
60	0,70	0,65	0,63									
70	0,73	0,67	0,64									
80	0,76	0,69	0,66	0,63								
90	0,79	0,72	0,68	0,64								
100	0,82	0,74	0,70	0,65	0,63							
120	0,87	0,79	0,74	0,68	0,65	0,63						
150	0,96	0,86	0,80	0,73	0,68	0,65	0,64	0,63				
160	1,00	0,88	0,82	0,74	0,70	0,66	0,65	0,63	0,62		0,63	
180		0,93	0,86	0,77	0,72	0,68	0,65	0,65	0,64	0,64	0,64	
200		1,00	0,90	0,80	0,74	0,69	0,67	0,66	0,65	0,65	0,65	
225			0,95	0,84	0,77	0,72	0,69	0,68	0,67	0,67	0,66	
240			1,00	0,86	0,79	0,73	0,71	0,69	0,69	0,68	0,67	
250				0,87	0,80	0,74	0,72	0,70	0,70	0,68	0,68	
275				0,91	0,83	0,76	0,74	0,72	0,72	0,70	0,69	
280				0,92	0,84	0,77	0,75	0,73	0,72	0,70	0,69	
300				0,95	0,86	0,79	0,76	0,74	0,74	0,72	0,71	
320				1,00	0,88	0,81	0,78	0,76	0,75	0,73	0,72	
350					0,92	0,83	0,81	0,78	0,78	0,75	0,73	
400					1,00	0,88	0,86	0,82	0,82	0,78	0,76	
440						0,92	0,89	0,85	0,85	0,81	0,79	
460						1,00	0,91	0,87	0,87	0,82	0,80	
500							0,95	0,90	0,90	0,85	0,82	
540							1,00	0,93	0,93	0,88	0,84	
560								1,00	0,95	0,89	0,86	
620									1,00	0,93	0,89	
660										1,00	0,91	
720											1,00	

EFFECT OF EDGE DISTANCE – TENSION

Edge Distance	Stud / Rebar Diameter											
(mm)	8	10	12	16	20	24	27	30	33	36	40	
40	0,64											
50	0,73	0,83										
60	0,82	0,70	0,63									
70	0,90	0,77	0,68									
80	100	0,84	0,74	0,63								
90		0,91	0,80	0,67								
100		100	0,86	0,71	0,63							
110			0,92	0,76	0,66							
120			100	0,80	0,70	0,64						
140				0,89	0,77	0,67	0,63	0,63				
160				100	0,84	0,72	0,70	0,65	0,62			
180					0,91	0,78	0,75	0,66	0,70	0,67	0,68	
200					100	0,84	0,81	0,76	0,76	0,78	0,71	
220						0,89	0,86	0,81	0,81	0,82	0,75	
240						100	0,92	0,86	0,86	0,87	0,78	
270							100	0,94	0,94	0,93	0,83	
280								100	0,97	0,96	0,85	
310									100	0,98	0,90	
330										100	0,93	
360											100	

EFFECT OF EDGE DISTANCE – SHEAR

Edge Distance	Stud / Rebar Diameter										
(mm)	8	10	12	16	20	24	27	30	33	36	40
40	0,25										
50	0,44	0,30									
60	0,63	0,48	0,30								
70	0,81	0,65	0,44								
80	100	0,83	0,58	0,40							
90		100	0,72	0,53							
100			0,86	0,67	0,35						
110			100	0,80	0,44						
125				100	0,58	0,35					
140					0,72	0,46	0,44	0,30			
160					0,91	0,62	0,57	0,35	0,34		
180					100	0,77	0,69	0,46	0,41	0,33	
200						0,92	0,82	0,57	0,50	0,42	0,32
220						100	0,94	0,68	0,59	0,51	0,53
240							100	0,78	0,68	0,60	0,59
280								100	0,86	0,78	0,72
310									100	0,91	0,82
330										100	0,89
360											100

POST INSTALLED REBAR CONNECTIONS

Minimum anchorage length 1) and lap splice length for C20/25 and maximum installation length (l_{max})

Rebar		$l_{b,min}$ (mm)	$l_{o,min}$ (mm)	$l_{max,min}$ (mm)
$\varnothing d_s$ (mm)	$f_{y,k}$ (N/mm ²)			
8	500	163	200	1000
10	500	204	204	1000
12	500	170	200	1200
14	500	198	210	1400
16	500	227	240	1600

1) According to EN 1992-1-1:2004 $l_{b,min}$ (8.6) and $l_{o,min}$ (8.11) for good bond conditions and $a_s = 1,0$ with maximum yield stress for rebar B500 B and $\gamma_M = 1,15$

DESIGN VALUES OF THE ULTIMATE BOND RESISTANCE FBD1) IN N/MM2 FOR ALL DRILLING METHODS FOR GOOD CONDITIONS

Rebar $\varnothing$	Concrete Class								
$\varnothing d_s$	C12/15	C16/20	C20/25	C25/30	C30/37	C35/45	C40/50	C45/60	C50/60
8 mm	1,6	1,6	1,6	1,6	1,6	1,6	1,6	1,6	1,6
10 mm	1,6	1,6	1,6	1,6	1,6	1,6	1,6	1,6	1,6
12 mm	1,6	2	2,3	2,3	2,3	2,3	2,3	2,3	2,3
14 mm	1,6	2	2,3	2,7	3	3,4	3,4	3,4	3,4
16 mm	1,6	2	2,3	2,7	3	3,4	3,7	4	4,3

1) Tabulated values for fbd are valid for good bond condition according to EN1992-1-1:2004. For all other bond conditions multiply the values for fbd by 0.7.

POST INSTALLED REBAR CONNECTIONS

Values for pre-calculation of anchoring

Rebar - Ø ds	$\alpha_1=\alpha_2=\alpha_3=\alpha_4=\alpha_5=1.0$			$\alpha_2 \text{ OR } \alpha_5=0.7; \alpha_1=\alpha_3=\alpha_4=1.0$		
	Anchorage length l_{bd}	Design value N_{rd}	Mortar volume	Anchorage length l_{bd}	Design value N_{rd}	Mortar volume
(mm)	(mm)	(kN)	(ml)	(mm)	(kN)	(ml)
8	163*	6,55	12	163*	9,42	12
	180	7,23	14	175	10,11	13
	250	10,05	19	190	10,98	14
	378	15,19	28	265	15,31	20
10	204*	10,25	18	204*	14,73	18
	220	11,05	20	220	15,89	20
	310	15,57	28	240	17,33	22
	390	19,59	35	280	20,22	25
	473	23,76	43	331	23,90	30
12	170*	14,74	18	170*	21,06	18
	270	23,41	29	230	28,49	24
	370	32,08	39	280	34,68	30
	470	40,75	50	340	42,12	36
	567	49,16	60	397	49,18	42
14	198*	20,03	24	198*	28,61	24
	310	31,36	37	260	37,57	31
	430	43,5	52	330	47,69	40
	550	55,64	66	400	57,81	48
	662	66,97	80	463	66,91	56
16	227*	26,24	31	227*	37,49	31
	360	41,62	49	300	49,55	41
	490	56,65	67	380	62,76	52
	620	71,68	84	450	74,32	61
	756	87,4	103	529	87,37	72

* Minimum anchorage length. The design value is valid for "good bond conditions" according to EN 1992-1-1.

All other condition: multiply value by 0.7. Mortar volume based on equation: $V = 1.2 \cdot (d_o^2 - d_d^2) \cdot \pi \cdot l_b / 4$

POST INSTALLED REBAR CONNECTIONS

Values for pre-calculation of overlap joints

Rebar - $\varnothing$ ds	$\alpha_1=\alpha_2=\alpha_3=\alpha_4=\alpha_5=1.0$			α_2 OR $\alpha_5=0.7$; $\alpha_1=\alpha_3=\alpha_4=1.0$		
	Anchorage length l_{bd}	Design value N_{rd}	Mortar volume	Anchorage length l_{bd}	Design value N_{rd}	Mortar volume
(mm)	(mm)	(kN)	(ml)	(mm)	(kN)	(ml)
8	200	8,04	15	200	11,56	15
	240	9,65	18	220	12,71	17
	290	11,66	22	230	13,29	17
	378	15,19	29	265	15,31	20
10	204	10,25	18	204	14,73	18
	270	13,56	24	230	16,61	21
	340	17,08	31	270	19,50	24
	400	20,10	36	300	21,67	27
	473	23,76	43	331	23,90	30
12	200	17,33	21	200	24,77	21
	290	25,13	31	250	30,97	26
	380	32,93	40	300	37,16	32
	480	41,60	51	350	43,35	37
	567	49,14	60	397	49,18	42
14	210	21,24	25	210	30,35	25
	320	32,37	39	270	39,02	33
	440	44,51	53	340	49,13	41
	550	55,64	66	400	57,81	48
	662	66,97	80	463	66,91	56
16	240	27,75	33	240	39,64	33
	370	42,78	50	310	51,2	42
	500	57,81	68	380	62,76	52
	630	72,83	86	460	75,97	62
	756	87,4	103	529	87,37	72

* Minimum anchorage length. The design value is valid for "good bond conditions" according to EN 1992-1-1.

All other condition: multiply value by 0.7. Mortar volume based on equation: $V = 1.2 \cdot (d_o^2 - d_d^2) \cdot \pi \cdot l_b / 4$